IN THE CLAIMS

Please amend the claims as follows:

1. (Withdrawn) A method of p-type doping in ZnO comprising:

forming an acceptor-doped material having ZnO under reducing conditions, thereby insuring a high donor density; and

annealing the specimens of said acceptor-doped material at intermediate temperatures under oxidizing conditions so as to remove intrinsic donors and activate impurity acceptors.

2. (Withdrawn) The method of claim 1, wherein said reducing conditions comprise a hydrogen containing atmosphere.

3. (Withdrawn) The method of claim 1, wherein said reducing conditions comprise a non- hydrogen containing atmosphere.

4. (Withdrawn) The method of claim 1, wherein said acceptor-doped material comprises a substrate, a n-type ZnO layer deposited on said substrate, and a p-type layer deposited on said n-type ZnO layer.

5. (Withdrawn) The method of claim 1, wherein said intermediate temperatures comprise a temperature range between 200 °C and 700 °C.

6. (Withdrawn) A method of forming p-n junctions using p-type ZnO comprising:

forming an acceptor-doped material having ZnO under reducing conditions, thereby insuring a high donor density; and

annealing the specimens of said acceptor-doped material at intermediate temperatures under oxidizing conditions so as to remove intrinsic donors and activate impurity acceptors.

7. (Withdrawn) The method of claim 6, wherein said reducing conditions comprise a hydrogen containing atmosphere.

8. (Withdrawn) The method of claim 6, wherein said reducing conditions comprise a non- hydrogen containing atmosphere.

9. (Withdrawn) The method of claim 6, wherein said acceptor-doped material comprises a substrate, a n-type ZnO layer deposited on said substrate, and a p-type layer deposited on said n-type ZnO layer.

10. (Withdrawn) The method of claim 6, wherein said intermediate temperatures comprises a temperature range between 200 °C and 700 °C.

11. (Currently Amended) A wide band gap semiconductor device comprising:

a substrate;

an annealed n-type ZnO layer directly ~~formed~~ positioned on said substrate; and

an annealed p-type ZnO layer directly ~~formed~~ positioned on said n-type ZnO layer, said annealed p-type ZnO comprises an acceptor-doped material under reducing conditions, said annealed n-type ZnO layer and said annealed p-type ZnO layer are annealed at intermediate temperatures under oxidizing conditions between approximately 200 °C and 700 °C to activate p-type conductivity~~;~~

~~wherein said n-type ZnO layer and said p-type ZnO layer are annealed in air to activate p-type conductivity~~.

12. (Currently Amended) The wide band gap semiconductor device of claim 11, wherein said ~~p-type ZnO layer is produced in reducing conditions comprising~~acceptor-doped material is exposed to a hydrogen containing atmosphere.

13. (Currently Amended) The wide band gap semiconductor device of claim 11, wherein said acceptor-doped material is exposed to ~~said p-type ZnO layer is produced in reducing conditions comprising~~ a non- hydrogen containing atmosphere.

14. (Cancelled).

15. (Cancelled).

16. (Currently Amended) A p-n junction comprising:

a substrate;

an annealed n-type ZnO layer directly ~~formed~~ positioned on said substrate; and

an annealed p-type ZnO layer directly ~~formed~~ positioned on said n-type ZnO layer, said annealed p-type ZnO comprises an acceptor-doped material under reducing conditions, said annealed n-type ZnO layer and said annealed p-type ZnO layer are annealed at intermediate temperatures under oxidizing conditions between approximately 200 °C and 700 °C to activate p-type conductivity~~;~~

~~wherein said n-type ZnO layer and said p-type ZnO layer are annealed in air to activate p-type conductivity~~.

17. (Currently Amended) The p-n junction of claim 16, said acceptor-doped material is exposed top ~~type ZnO layer is produced in reducing conditions comprising~~ a hydrogen containing atmosphere .

18. (Currently Amended) The p-n junction of claim 16, wherein said acceptor-doped material is exposed top ~~type ZnO layer is produced in reducing conditions comprising~~ a non- hydrogen containing atmosphere .

19. (Cancelled) .

20. (Cancelled)